

Bentoproof Injekt PLUS

Hydrophilic injection hose system

TECHNICAL DATASHEET

Status 31.07.2020

Item no.: S04520040

an.kox GmbH

72108 Rottenburg a. N. www.an-kox.de

PROPERTIES

Bentoproof Injekt PLUS is a combination of two active joint sealant systems including a protective coating for sealing construction joints in concrete structures.

Bentoproof Injekt PLUS contains two components: the certificated injection hose WaterproofX[®] 1 and the certificated hydrophilic water bar Bentoproof black PLUS. This combination guarantees a maximum of reliability and impermeability.

APPLICATION

Within this system the bentonite hydrophilic water bar takes on the immediate, sealing task. The material changes from its solid state into a plastic compound, allowing it to penetrate the finest of cracks and cavities. If increasing of the volume is obstructed, a swelling pressure will be created which finally engages the sealing. The injection hose WaterproofX[®] 1 which is placed in the core of the bentonite hydrophilic water bar can be injected additionally if necessary (numerous injection cycles are possible). Thus this system fulfills the highest quality demands.

The protective coating of **Bentoproof Injekt PLUS** prevents the bentonite water bar to start swelling untimely. Thus the installation is totally independent on atmospheric conditions. The hardening process of the concrete will dissolve the protective coating.

Bentoproof Injekt PLUS is available in a handsome Bentoproof Injekt PLUS Set 5x8 m, including all required accessories.

TECHNICAL DATA

Profile:	external dimension: core dimension:	20 x 25 mm 13 mm external, 6 mm internal
Consistency hull:	ductile	
Colour:	hull: black core: blue	
Temperature resistance:	-20°C / +70°C	

PACKAGING & STORAGE

20 x 25 mm

carton: 40 m (5 coils à 8 m)

pallet: 720 m

Junghansring 52

Bentoproof Injekt PLUS has to be stored in a dry place and protected against mechanical damage.



Bentoproof Injekt PLUS

Hydrophilic injection hose system

TECHNICAL DATASHEET

Status 31.07.2020

an.kox GmbH

72108 Rottenburg a. N. www.an-kox.de

Junghansring 52

Item no.: S04520040

INSTALLATION

The concrete surface must be dry, free of dust, forming oil rest and loose particles and must not show any sharp-edged displacement. Before installing **Bentoproof Injekt PLUS** ice coverings, standing water and cement sludge have to be removed.

Bentoproof Injekt PLUS can either be installed with clamps, with Contact adhesive SuperX 1 or with a special fixing mesh on the first concrete section in the middle of the joint in between the reinforcements. The distance in between two neighboring clamps is depending on the state of the surface. The maximum distance of 15 cm must not be exceeded to ensure that Bentoproof Injekt PLUS is securely fixed in place and will remain so during concreting. Lightly pushing the water bar into the Contact adhesive SuperX 1 ensures optimum fixing. If Bentoproof Injekt PLUS is fixed with the special fixing mesh, wall plugs arm the mesh on its external section.

The ventilation edges are driven right-angled out of the construction. They are joined together at the Varioclix[®], which can be installed on the reinforcement or be fixed on the formwork. A check mark of the edges and a protected position of the circuit points have to be assured for the injection of the hose at a later date. The minimal covering of concrete must be at least 8 to 10 cm on all sides. This ensures that the necessary expansion and sealing effect can be achieved.

Unevenness can be adjusted with the **Polymer-swellingpaste SX® 100**. With the application of the bentonite hydrophilic water bar uneven sections on the concrete surface are leveled out. Thereby a complete contact of the concrete surface and the combined swell-injection system can be achieved. At sections and circuit points **Bentoproof Injekt PLUS** is installed 10 cm flush next to each other.

Damages on the system (swelling before installation, buckling, holes, cuts, etc.) may lead to uselessness which makes the system to be replaced before being installed.

For the injection, the temperature of the parts as well as outside has to be > $+5^{\circ}$ C..

ACCESSORIES

Item no. S04520040	Bentoproof Injekt PLUS Set 5x8 m
ltem no. S04900001	Hose connector
ltem no. S04820050	PVC hose white
Item no. S04700000	Varioclix®
Item no. S02830290	Contact adhesive SuperX 1 cartridge 290 ml
Item no. S02410290	Polymer-swellingpaste SX® 100 cartridge 290 ml

<u>Note</u>:

The information on this data sheet is based on our experience and given to the best of our knowledge, but is not legally binding. Recommendations, which are at variance with those stated in this data sheet, are only binding for us, when confirmed in writing. The manufacturer is not responsible for damages resulting from the misuse or incorrect storage of the product. For the accuracy of this information we are liable within the scope of our delivery and service conditions. Creation date: 07/2020